



PED Certified | OHSAS 18001:2007 | ISO 9001 : 2008 | ISO 14001:2004
| Govt. Recog. Export House.

**Manufacturer, Exporter, Stockiest, Supplier, Trader for
Carbon Steel, Stainless Steel, Alloy Steel And High Nickel Alloy,
Nickel Alloy Plate, Sheets And Coils.**



Standard Specification for Structural Steel for Bridges¹

This standard is issued under the fixed designation A 709/A 709M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers carbon and high-strength low-alloy steel structural shapes, plates, and bars and quenched and tempered alloy steel for structural plates intended for use in bridges. Seven grades are available in four yield strength levels as follows:

| Grade U.S. [SI] | Yield Strength, ksi [MPa] |
|---------------------|---------------------------|
| 36 [250] | 36 [250] |
| 50S [345S] | 50 [345] |
| 50W [345W] | 50 [345] |
| HPS 50W [HPS 345W] | 50 [345] |
| HPS 70W [HPS 485W] | 70 [485] |
| HPS 100W [HPS 690W] | 100 [690] |

1.1.1 Grades 36 [250], 50 [345], 50S [345S], and 50W [345W] are also included in Specifications [A 36/A 36M](#), [A 572/A 572M](#), [A 992/A 992M](#), and [A 588/A 588M](#), respectively. When the supplementary requirements of this specification are specified, they exceed the requirements of Specifications [A 36/A 36M](#), [A 572/A 572M](#), [A 992/A 992M](#), and [A 588/A 588M](#).

1.1.2 Grades 50W [345W], HPS 50W [HPS 345W], HPS 70W [HPS 485W], and HPS 100W [HPS 690W] have enhanced atmospheric corrosion resistance (see [13.1.2](#)). Product availability is shown in [Table 1](#).

1.2 Grade HPS 70W [HPS 485W] or HPS 100W [HPS 690W] shall not be substituted for Grades 36 [250], 50 [345], 50S [345S], 50W [345W], or HPS 50W [HPS 345W]. Grade 50W [345W], or HPS 50W [HPS 345W] shall not be substituted for Grades 36 [250], 50 [345] or 50S [345S] without agreement between the purchaser and the supplier.

1.3 When the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized. See Appendix X3 of Specification [A 6/A 6M](#) for information on weldability.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock and Ships.

Current edition approved April 1, 2009. Published April 2009. Originally approved in 1974. Last previous edition approved in 2008 as A 709/A 709M – 08.

1.4 For structural products to be used as tension components requiring notch toughness testing, standardized requirements are provided in this standard, and they are based upon American Association of State Highway and Transportation Officials (AASHTO) requirements for both fracture critical and non-fracture critical members.

1.5 Supplementary requirements are available but shall apply only if specified in the purchase order.

are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.7 For structural products produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification [A 6/A 6M](#) apply.

2. Referenced Documents

2.1 ASTM Standards:²

- [A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling](#)
- [A 36/A 36M Specification for Carbon Structural Steel](#)
- [A 370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)
- [A 572/A 572M Specification for High-Strength Low-Alloy Columbium-Vanadium Structural Steel](#)
- [A 588/A 588M Specification for High-Strength Low-Alloy Structural Steel, up to 50 ksi \[345 MPa\] Minimum Yield Point, with Atmospheric Corrosion Resistance](#)
- [A 673/A 673M Specification for Sampling Procedure for Impact Testing of Structural Steel](#)
- [A 992/A 992M Specification for Structural Steel Shapes](#)

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Tensile and Hardness Requirements^A

NOTE 1—Where “. . .” appears in this table, there is no requirement.

| Grade | Plate Thickness, in. [mm] | Structural Shape Flange or Leg Thickness, in. [mm] | Yield Point or Yield Strength, ^B ksi [MPa] | Tensile Strength, ksi [MPa] | Minimum Elongation, % | | | | Reduction of Area ^{C,D} min, % |
|-----------------------------------|-------------------------------|--|---|---|--------------------------------|-----------------|---------------------|-----------------------|---|
| | | | | | Plates and Bars ^{C,E} | | Shapes ^E | | |
| | | | | | 8 in. or 200 mm | 2 in. or 50 mm | 8 in. or 200 mm | 2 in. or 50 mm | |
| 36 [250] | to 4 [100], incl | to 3 in. [75 mm], incl over 3 in. [75 mm] | 36 [250] min 36 [250] min | 58–80 [400–550] 58 [400] min | 20 ... | 23 .. | 20 20 | 21 19 | |
| 50 [345] 50S [345S] | to 4 [100], incl ^G | all all | 50 [345] min 50–65 [345–450] ^{H,I} 50 [345] min | 65 [450] min 65 [450] ^H min | 18 ... | 21 ... | 18 18 | 21 ^F 21 | |
| 50W [345W] and HPS 50W [HPS 345W] | to 4 [100], incl | all | 50 [345] min | 70 [485] min | 18 | 21 | 18 | 21 ^J | ... |
| HPS 70W [HPS 485 W] | to 4 [100], incl | ^G | 70 [485] min ^B | 85–110 [585–760] | ... | 19 ^K | ... | ... | ... |
| HPS 100W [HPS 690W] | to 2½ [65], incl | ^G | 100 [690] min ^B | 110–130 [760–895] | ... | 18 ^K | ... | ... | ^L |

^A See specimen orientation and preparation subsection in the Tension Tests section of Specification A 6/A 6M.

^B Measured at 0.2 % offset or 0.5 % extension under load as described in Section 13 of Test Methods A 370.

^C Elongation and reduction of area not required to be determined for floor plates.

^D For plates wider than 24 in. [600 mm], the reduction of area requirement, where applicable, is reduced by five percentage points.

^E For plates wider than 24 in. [600 mm], the elongation requirement is reduced by two percentage points. See elongation requirement adjustments in the Tension Tests section of Specification A 6/A 6M.

^F Elongation in 2 in. or 50 mm: 19 % for shapes with flange thickness over 3 in. [75 mm].

^G Not applicable.

^H The yield to tensile ratio shall be 0.87 or less for shapes that are tested from the web location; for all other shapes, the requirement is 0.85.

^I A maximum yield strength of 70 ksi [480 MPa] is permitted for structural shapes that are required to be tested from the web location.

^J For wide flange shapes with flange thickness over 3 in. [75 mm], elongation in 2 in. or 50 mm of 18 % minimum applies.

^K If measured on the Fig. 3 (Test Methods A 370) 1½-in. [40-mm] wide specimen, the elongation is determined in a 2-in. or 50-mm gage length that includes the fracture and shows the greatest elongation.

^L 40 % minimum applies if measured on the Fig 3 (Test Methods A 370) 1½-in. [40-mm] wide specimen; 50 % minimum applies if measured on the Fig. 4 (Test Methods A 370) ½-in. [12.5-mm] round specimen.

TABLE 2 Grade 36 [250] Chemical Requirements (Heat Analysis)

NOTE 1—Where “. . .” appears in this table there is no requirement. The heat analysis for manganese shall be determined and reported as described in the Heat Analysis section of Specification A 6/A 6M.

| Product Thickness, in. (mm) | Shapes ^A All | Plates ^B | | | | Bars ^B | | |
|---|-------------------------|---------------------|-------------------------------|--------------------------------|--------------------------------|-------------------|-------------------------------|--------------------------|
| | | To ¾ [20], incl | Over ¾ to 1½ [20 to 40], incl | Over 1½ to 2½ [40 to 65], incl | Over 2½ to 4 [65 to 100], incl | To ¾ [20], incl | Over ¾ to 1½ [20 to 40], incl | Over 1½ to 4 [100], incl |
| Carbon, max, % | 0.26 | 0.25 | 0.25 | 0.26 | 0.27 | 0.26 | 0.27 | 0.28 |
| Manganese, % | ... | ... | 0.80–1.20 | 0.80–1.20 | 0.85–1.20 | ... | 0.60–0.90 | 0.60–0.90 |
| Phosphorus, max, % | 0.04 | 0.04 | 0.04 | 0.04 | 0.04 | 0.04 | 0.04 | 0.04 |
| Sulfur, max, % | 0.05 | 0.05 | 0.05 | 0.05 | 0.05 | 0.05 | 0.05 | 0.05 |
| Silicon, % | 0.40 max | 0.40 max | 0.40 max | 0.15–0.40 | 0.15–0.40 | 0.40 max | 0.40 max | 0.40 max |
| Copper, min, % when copper steel is specified | 0.20 | 0.20 | 0.20 | 0.20 | 0.20 | 0.20 | 0.20 | 0.20 |

^A Manganese content of 0.85 to 1.35 % and silicon content of 0.15 to 0.40 % is required for shapes with flange thickness over 3 in. [75 mm].

^B For each reduction of 0.01 % below the specified carbon maximum, an increase of 0.06 % manganese above the specified maximum will be permitted up to a maximum of 1.35 %.

G 101 Guide for Estimating the Atmospheric Corrosion Resistance of Low-Alloy Steels

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 fracture critical member—a main load-carrying tension member or tension component of a bending member whose failure would be expected to cause collapse of a structure or bridge without multiple, redundant load paths.

3.1.2 main load-carrying member—a steel member designed to carry primary design loads, including dead, live, impact, and other loads.

3.1.3 non-fracture critical member—a main load-carrying member whose failure would not be expected to cause collapse of a structure or bridge with multiple, redundant load paths.

3.1.4 non-tension component—a steel member that is not in tension under any design loading.

3.1.5 secondary member—a steel member used for aligning and bracing of main load-carrying members, or for attaching utilities, signs, or other items to them, but not to directly support primary design loads

3.1.6 tension component—a part or element of a fracture critical or non-fracture critical member that is in tension under various design loadings.

TABLE 3 Grade 50 [345] Chemical Requirements^A (Heat Analysis)

| Maximum Diameter, Thickness, or Distance Between Parallel Faces, in. [mm] | Carbon, max, % | Manganese, ^B max, % | Phosphorus, max, % | Sulfur, max, % | Silicon ^C | | Columbium, Vanadium and Nitrogen |
|---|----------------|--------------------------------|--------------------|----------------|--|---|----------------------------------|
| | | | | | Plates to 1½-in. [40-mm] Thick, Shapes with flange or leg thickness to 3 in. [75 mm] inclusive, Sheet Piling, Bars, Zees, and Rolled Tees, max, % ^D | Plates Over 1½-in. [40-mm] Thick and Shapes with flange thickness over 3 in. [75 mm], % | |
| 4 [100] | 0.23 | 1.35 | 0.04 | 0.05 | 0.40 | 0.15–0.40 | ^E |

^A Copper when specified shall have a minimum content of 0.20 % by heat analysis (0.18 % by product analysis).

^B Manganese, minimum by heat analysis of 0.80 % (0.75 % by product analysis) shall be required for all plates over ¾ in. [10 mm] in thickness; a minimum of 0.50 % (0.45 % by product analysis) shall be required for plates ¾ in. [10 mm] and less in thickness, and for all other products. The manganese to carbon ratio shall not be less than 2 to 1. For each reduction of 0.01 percentage point below the specified carbon maximum, an increase of 0.06 percentage point manganese above the specified maximum is permitted, up to a maximum of 1.60 %.

^C Silicon content in excess of 0.40 % by heat analysis must be negotiated.

^D Bars over 1½ in. [40 mm] in diameter, thickness, or distance between parallel faces, shall be made by a killed steel practice.

^E Alloy content shall be in accordance with Type 1, 2, 3, or 5 and the contents of the applicable elements shall be reported on the test report.

| Type | Elements | Heat Analysis, % |
|------|-------------------------|-------------------------|
| 1 | Columbium ^A | 0.005–0.05 ^B |
| 2 | Vanadium | 0.01–0.15 |
| 3 | Columbium ^A | 0.005–0.05 ^B |
| | Vanadium | 0.01–0.15 |
| 5 | Columbium plus vanadium | 0.02–0.15 ^C |
| | Titanium | 0.006–0.04 |
| | Nitrogen | 0.003–0.015 |
| | Vanadium | 0.06 max |

^A Columbium shall be restricted to Grade 50 [345] plate, bar, zee, and rolled tee thickness of ¾ in. [20 mm] max, and to shapes with flange or leg thickness to 1½ in. [40 mm] inclusive unless killed steel is furnished. Killed steel shall be confirmed by a statement of killed steel on the test report, or by a report of the presence of a sufficient quantity of a strong deoxidizing element, such as silicon at 0.10 % or higher, or aluminum at 0.015 % or higher.

^B Product analysis limits = 0.004 to 0.06 %.

^C Product analysis limits = 0.01 to 0.16 %.

TABLE 4 Grade 50W [345 W] Chemical Requirements (Heat Analysis)

NOTE 1—Types A, B, and C are equivalent to Specification A 588/A 588M Grades A, B, and C, respectively.

| Element | Composition, % ^A | | |
|------------------------|-----------------------------|-----------|-----------|
| | Type A | Type B | Type C |
| Carbon ^B | 0.19 max | 0.20 max | 0.15 max |
| Manganese ^B | 0.80–1.25 | 0.75–1.35 | 0.80–1.35 |
| Phosphorus | 0.04 max | 0.04 max | 0.04 max |
| Sulfur | 0.05 max | 0.05 max | 0.05 max |
| Silicon | 0.30–0.65 | 0.15–0.50 | 0.15–0.40 |
| Nickel | 0.40 max | 0.50 max | 0.25–0.50 |
| Chromium | 0.40–0.65 | 0.40–0.70 | 0.30–0.50 |
| Copper | 0.25–0.40 | 0.20–0.40 | 0.20–0.50 |
| Vanadium | 0.02–0.10 | 0.01–0.10 | 0.01–0.10 |

^A Weldability data for these types have been qualified by FHWA for use in bridge construction.

^B For each reduction of 0.01 percentage point below the specified maximum for carbon, an increase of 0.06 percentage point above the specified maximum for manganese is permitted, up to a maximum of 1.50 %.

4. Ordering Requirements

4.1 In addition to the items listed in the ordering information section of Specification A 6/A 6M, the following items should be considered if applicable:

TABLE 5 Grades HPS 50W [HPS 345W] and HPS 70W [HPS 485 W], and HPS 100W [HPS 690W] Chemical Requirements (Heat Analysis)

NOTE 1—Where “. . .” appears in this table, there is no requirement.

| Element | Composition, % | |
|---------------------------|--|---------------------------|
| | Grades | |
| | HPS 50W [HPS 345W], HPS 70W [HPS 485W] | Grade HPS 100W [HPS 690W] |
| Carbon | 0.11 max | 0.08 max |
| Manganese | | |
| 2.5 in. [65 mm] and under | 1.10–1.35 | 0.95–1.50 |
| Over 2.5 in. [65 mm] | 1.10–1.50 | ^A |
| Phosphorus | 0.020 max | 0.015 max |
| Sulfur ^B | 0.006 max | 0.006 max |
| Silicon | 0.30–0.50 | 0.15–0.35 |
| Copper | 0.25–0.40 | 0.90–1.20 |
| Nickel | 0.25–0.40 | 0.65–0.90 |
| Chromium | 0.45–0.70 | 0.40–0.65 |
| Molybdenum | 0.02–0.08 | 0.40–0.65 |
| Vanadium | 0.04–0.08 | 0.04–0.08 |
| Columbium (Niobium) | . . . | 0.01–0.03 |
| Aluminum | 0.010–0.040 | 0.020–0.050 |
| Nitrogen | 0.015 max | 0.015 max |

^A Not applicable.

^B The steel shall be calcium treated for sulfide shape control.

**TABLE 6 Grade 50S [345S] Chemical Requirements
(Heat Analysis)**

| Element | Composition, % |
|-----------------|---------------------------|
| Carbon, max | 0.23 |
| Manganese | 0.50 to 1.60 ^A |
| Silicon, max | 0.40 |
| Vanadium, max | 0.15 ^B |
| Columbium, max | 0.05 ^B |
| Phosphorus, max | 0.035 |
| Sulfur, max | 0.045 |
| Copper, max | 0.60 |
| Nickel, max | 0.45 |
| Chromium, max | 0.35 |
| Molybdenum, max | 0.15 |

^A Provided that the ratio of manganese to sulfur is not less than 20 to 1, the minimum limit for manganese for shapes with flange or leg thickness not exceeding 1 in. [25 mm] shall be 0.30 %.

^B The sum of columbium and vanadium shall not exceed 0.15 %.

**TABLE 7 Relationship Between Impact Testing Temperature
Zones and Minimum Service Temperature**

| Zone | Minimum Service Temperature, °F [°C] |
|------|--------------------------------------|
| 1 | 0 [-18] |
| 2 | below 0 to -30 [-18 to -34] |
| 3 | below -30 to -60 [-34 to -51] |

4.1.1 Type of component (tension or non-tension, fracture critical or non-fracture critical) (see Section 10).

4.2 Impact testing temperature zone (see Table 7).

5. General Requirements for Delivery

5.1 Structural products furnished under this specification shall conform to the requirements of the current edition of Specification A 6/A 6M, for the specific structural product ordered, unless a conflict exists in which case this specification shall prevail.

5.2 Coils are excluded from qualification to this specification until they are processed into a finished structural product. Structural products produced from coil means structural products that have been cut to individual lengths from a coil. The processor directly controls, or is responsible for, the operations involved in the processing of a coil into a finished structural product. Such operations include decoiling, leveling or straightening, hot-forming or cold-forming (if applicable), cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 1—For structural products produced from coil and furnished without heat treatment or with stress relieving only, two test results are to be reported for each qualifying coil. Additional requirements regarding structural products produced from coil are described in Specification A 6/A 6M.

6. Materials and Manufacture

6.1 For Grades 36 [250] and 50 [345], the steel shall be semi-killed or killed.

6.2 For Grades 50W [345W], HPS 50W [HPS 345W], and HPS 70W [HPS 485W], the steel shall be made to fine grain practice.

6.3 For Grade 50S [345S], the steel shall be killed and such shall be affirmed in the test report by a statement of *killed steel*,

a value of 0.10 % or more for the silicon content, or a value of 0.015 % or more for the total aluminum content.

6.4 For Grade 50S [345S], the steelmaking practice used shall be one that produces steel having a nitrogen content not greater than 0.015 % and includes the addition of one or more nitrogen-binding elements, or one that produces steel having a nitrogen content of not greater than 0.012 % (with or without the addition of nitrogen-binding elements). The nitrogen content need not be reported, regardless of which steelmaking practice was used.

6.5 For Grades HPS 50W [HPS 345W], HPS 70W [HPS 485W], and HPS 100W [HPS 690W], the steel shall be made using a low-hydrogen practice, such as vacuum degassing during steel making; controlled soaking of the ingots, slabs; controlled slow cooling of the ingots, slabs, or plates, or a combination thereof.

6.6 For Grade HPS 100W [HPS 690W], the requirements for fine austenitic grain size in Specification A 6/A 6M shall be met.

6.7 Grades HPS 50W [HPS 345W] and HPS 70W [HPS 485W] shall be furnished in one of the following conditions: as-rolled, control-rolled, thermo-mechanical control processed (TMCP) with or without accelerated cooling, or quenched and tempered.

7. Heat Treatment

7.1 For quenched and tempered Grades HPS 50W [HPS 345W] and HPS 70W [HPS 485W], the heat treatment shall be performed by the manufacturer and shall consist of heating the steel to not less than 1650°F [900°C], quenching it in water or oil, and tempering it at not less than 1100°F [590°C]. The heat-treating temperatures shall be reported on the test certificates.

7.2 For Grade HPS 100W [HPS 690W], the heat treatment shall be performed by the manufacturer and shall consist of heating the steel to a temperature in the range from 1600 to 1700°F [870 to 925°C], quenching it in water, and tempering it at not less than 1050°F [565°C] for a time to be determined by the manufacturer. The heat-treating temperatures shall be reported on the test certificates.

8. Chemical Requirements

8.1 The heat analysis shall conform to the requirements for the specified grade, as given in Tables 2-6.

8.2 For Grade 50S [345S], in addition to the elements listed in Table 6, test reports shall include, for information, the chemical analysis for tin. Where the amount of tin is less than 0.02 %, it shall be permissible for the analysis to be reported as <0.02 %.

8.3 For Grade 50S [345S], the maximum permissible carbon equivalent value shall be 0.47 % for structural shapes with flange thickness over 2 in. [50 mm], and 0.45 % for other structural shapes. The carbon equivalent shall be based on heat analysis. The required chemical analysis as well as the carbon equivalent shall be reported. The carbon equivalent shall be calculated using the following formula:

$$CE = C + \frac{Mn}{6} + \frac{1}{5} \frac{Si + Cr + Mo + V}{5} + \frac{1}{15} \frac{Ni + Cu}{15} \quad (1)$$

9. Tensile Requirements

9.1 The material as represented by test specimens, except as specified in 9.2, shall conform to the requirements for tensile properties given in Table 1.

9.2 For Grade 36 [250], shapes less than 1 in.² [645 mm²] in cross section and bars, other than flats, less than ½ in. [12.5 mm] in thickness or diameter need not be subjected to tension tests by the manufacturer.

10. Impact Testing Requirements

10.1 *Non-Fracture-Critical, T, Tension Components*—Structural products ordered for use as tension components of non-fracture-critical members shall be impact tested in accordance with Specification A 673/A 673M and as given in Table 8. The test results shall meet the requirements given in Table 8.

10.2 *Fracture-Critical, F, Tension Components*—Structural products ordered for use as tension components of fracture-critical members shall be impact tested in accordance with Specification A 673/A 673M and as given in Table 9. The test results shall meet the requirements given in Table 9.

10.3 Steel grades ordered for use without suffix T or F as listed in 9.1 and 9.2 do not require impact testing and shall be used as non-tension components or secondary members only.

11. Test Specimens and Number of Tension Tests

11.1 For Grades 36 [250], 50 [345], and 50W [345W], and non-quenched and tempered Grades HPS 50W [HPS 345W] and HPS 70W [HPS 485W], location and condition, number of tests, and preparation of test specimens shall meet the requirements of Specification A 6/A 6M.

11.2 The following requirements, which are in addition to those of Specification A 6/A 6M, shall apply only to Grade HPS 100W [HPS 690W] and quenched and tempered Grades HPS 50W [HPS 345W] and HPS 70W [HPS 485W].

11.2.1 When possible, all test specimens shall be cut from the plate in its heat-treated condition. If it is necessary to prepare test specimens from separate pieces, all of these pieces

shall be full thickness, and shall be similarly and simultaneously heat treated with the material. All such separate pieces shall be of such size that the prepared test specimens are free of any variation in properties due to edge effects.

11.2.2 After final heat treatment of the plates, one tension test specimen shall be taken from a corner of each plate as heat treated.

NOTE 2—The term “plate” identifies the “plate as heat treated.”

12. Retests

12.1 Grades 36 [250], 50 [345], 50S [345S], and 50W [345W], and non-quenched and tempered HPS 50W [HPS 345W] and HPS 70W [HPS 485W] shall be retested in accordance with Specification A 6/A 6M.

12.2 The manufacturer may reheat treat quenched and tempered plates that fail to meet the mechanical property requirements of this specification. All mechanical property tests shall be repeated when the material is resubmitted for inspection.

13. Atmospheric Corrosion Resistance

13.1 Steels meeting this specification provide two levels of atmospheric corrosion resistance:

13.1.1 Steel grades without suffix provide a level of atmospheric corrosion resistance typical of carbon or alloy steel without copper.

13.1.2 The steel for Grades 50W [345W], HPS 50W [HPS 345W], and HPS 70W [HPS 485W] shall have an atmospheric corrosion resistance index of 6.0 or higher, calculated from the heat analysis in accordance with Guide G 101, Predictive Method Based on the Data of Larabee and Coburn (see Note 3). When properly exposed to the atmosphere, these steels can be used bare (unpainted) for many applications. The steel for Grade HPS 100W [HPS 690W] provides an improved level of atmospheric corrosion resistance over alloy steel without copper.

TABLE 8 Non-Fracture Critical Tension Component Impact Test Requirements

| Grade | Thickness, in. [mm] | Minimum Average Energy, ft-lbf [J] | | |
|--|--|--|--|--|
| | | Zone 1 | Zone 2 | Zone 3 |
| 36T [250T] ^A | to 4 [100] incl | 15 [20] at 70°F [21°C] | 15 [20] at 40°F [4°C] | 15 [20] at 10°F [−12°C] |
| 50T [345T] ^{A, B} 50ST [345ST] ^{A, B} 50WT [345WT] ^{A, B} | to 2 [50] incl over 2 to 4 [50 to 100] incl | 15 [20] at 70°F [21°C] 20 [27] at 70°F [21°C] | 15 [20] at 40°F [4°C] 20 [27] at 40°F [4°C] | 15 [20] at 10°F [−12°C] 20 [27] at 10°F [−12°C] |
| HPS 50WT [HPS 345WT] ^{A, B} | to 4 [100] incl | 20 [27] at 10°F [−12°C] | 20 [27] at 10°F [−12°C] | 20 [27] at 10°F [−12°C] |
| HPS 70WT [HPS 485WT] ^{C, D} | to 4 [100] incl | 25 [34] at −10°F [−23°C] | 25 [34] at −10°F [−23°C] | 25 [34] at −10°F [−23°C] |
| HPS 100WT [HPS 690WT] ^C | to 2½ [65] incl over 2½ to 4 [65 to 100] incl | 25 [34] at −30°F [−34°C] 35 [48] at −30°F [−34°C] | 25 [34] at −30°F [−34°C] 35 [48] at −30°F [−34°C] | 25 [34] at −30°F [−34°C] 35 [48] at −30°F [−34°C] |

^A The CVN-impact testing shall be at “H” frequency in accordance with Specification A 673/A 673M.

^B If the yield point of the structural product exceeds 65 ksi [450 MPa], the testing temperature for the minimum average energy required shall be reduced by 15°F [8°C] for each increment of 10 ksi [70 MPa] above 65 ksi [450 MPa]. The yield point is the value given in the test report.

^C The CVN-impact testing shall be at “P” frequency in accordance with Specification A 673/A 673M.

^D If the yield strength of the structural product exceeds 85 ksi [585 MPa], the testing temperature for the minimum average energy required shall be reduced by 15°F [8°C] for each increment of 10 ksi [70 MPa] above 85 ksi [585 MPa]. The yield strength is the value given in the test report.

TABLE 9 Fracture Critical Tension Component Impact Test Requirements

| Grade | Thickness, in. [mm] | Minimum Test Value Energy, ^A ft-lbf [J] | Minimum Average Energy ^A , ft-lbf [J] | | |
|---|--|--|---|---|---|
| | | | Zone 1 | Zone 2 | Zone 3 |
| 36F [250F] | to 4 [100] incl | 20 [27] | 25 [34] at 70°F [21°C] | 25 [34] at 40°F [4°C] | 25 [34] at 10°F [-12°C] |
| 50F [345F] ^B , 50SF [345SF] ^B , 50WF [345WF] ^B | to 2 [50] incl over 2 to 4 [50 to 100] incl | 20 [27] 24 [33] | 25 [34] at 70°F [21°C] 30 [41] at 70°F [21°C] | 25 [34] at 40°F [4°C] 30 [41] at 40°F [4°C] | 25 [34] at 10°F [-12°C] 30 [41] at 10°F [-12°C] |
| HPS 50WF [HPS 345WF] ^B HPS 70WF [HPS 485WF] ^C | to 4 [100] incl to 4 [100] incl | 24 [33] 28 [38] | 30 [41] at 10°F [-12°C] 35 [48] at -10°F [-23°C] | 30 [41] at 10°F [-12°C] 35 [48] at -10°F [-23°C] | 30 [41] at 10°F [-12°C] 35 [48] at -10°F [-23°C] |
| HPS 100WF [HPS 690WF] | to 2 ½ [65] incl | 28 [38] | 35 [48] at -30°F [-34°C] | 35 [48] at -30°F [-34°C] | 35 [48] at -30°F [-34°C] |

^A The CVN-impact testing shall be at “P” frequency in accordance with Specification **A 673/A 673M** except for plates of Grades 36F [250F], 50F [345F], 50WF [345WF], HPS 50WF [HPS 345WF], and HPS 70WF [HPS 485WF], for which the sampling shall be as follows:

- (1) As-rolled (including control-rolled and TMCP) plates shall be sampled at each end of each plate-as-rolled.
- (2) Normalized plates shall be sampled at one end of each plate, as heat treated.
- (3) Quenched and tempered plates shall be sampled at each end of each plate, as heat treated.

^B If the yield point of the structural product exceeds 65 ksi [450 MPa], the testing temperature for the minimum average energy and minimum test value energy required shall be reduced by 15°F [8°C] for each increment of 10 ksi [70 MPa] above 65 ksi [450 MPa]. The yield point is the value given in the test report.

^C If the yield strength of the structural product exceeds 85 ksi [585 MPa], the testing temperature for the minimum average energy and minimum test value energy required shall be reduced by 15°F [8°C] for each increment of 10 ksi [70 MPa] above 85 ksi [585 MPa]. The yield strength is the value given in the test report.

NOTE 3—For methods of estimating the atmospheric corrosion resistance of low-alloy steels, see Guide **G 101**. The user is cautioned that the Guide **G 101** predictive equation (Predictive Method Based on the Data of Larabee and Coburn) for calculation of an atmospheric corrosion resistance index has only been verified for the composition limits stated in that guide.

14. Marking

14.1 In addition to the marking requirements of Specification **A 6/A 6M**, the structural product shall be marked as follows:

14.1.1 For Grade 50W [345W], the composition type shall be included.

14.1.2 For structural products that conform to the requirements of **10.1**, the letter *T* and the applicable zone number (1, 2, or 3) shall follow the grade designation.

14.1.3 For structural products that conform to the requirements of **10.2**, the letter *F* and the applicable zone number (1, 2, or 3) shall follow the grade designation.

15. Keywords

15.1 alloy; atmospheric corrosion resistance; bars; bridges; carbon; fracture-critical; high-strength; low-alloy; non-fracture critical; plates; quenched; shapes; steel; structural steel; tempered

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the purchase order or contract. Standardized supplementary requirements for use at the option of the purchaser are listed in Specification **A 6/A 6M**. Those that are considered suitable for use with this specification are listed by title:

S8. Ultrasonic Examination

S5.1 Refer to S8 of Specification **A 6/A 6M**.

S32. Single Heat Bundles

S32.1 Bundles containing shapes or bars shall be from a single heat of steel.

S60. Frequency of Tension Tests

S60.1 Tension testing that is additional to the tension testing required by Specification **A 6/A 6M** shall be made, as follows:

S60.1.1 *Plate*—One tension test shall be made using a test specimen taken from each as-rolled or as-heat treated plate.

S60.1.2 *Structural Shapes*—One tension test shall be made using a test specimen taken from each 5 tons [5 Mg] of material produced on the same mill of the same nominal size, excluding length, from each heat of steel. For single pieces that weigh more than 5 tons [5 Mg] individually, each piece shall be tested. If shapes are heat treated, one test shall be made on specimens taken from each heat of the same nominal size, excluding length, in each furnace lot.

S60.1.3 *Bars*—One tension test shall be made using a test specimen taken from each 5 tons [5 Mg] of the same heat and same diameter or thickness if the material is furnished as-rolled or is heat treated in a continuous-type furnace. For material heat treated in other than a continuous-type furnace, one test

shall be taken from each heat of the same bar diameter or thickness for each furnace charge.

S92. Atmospheric Corrosion Resistance

S92.1 When specified, the material manufacturer shall supply to the purchaser evidence of atmospheric corrosion resistance satisfactory to the purchaser.

S92.2 Refer to S23 of Specification **A 6/A 6M** (applicable only to Grades 36 [250] and 50 [345]).

S93. Limitation on Weld Repair (Fracture Critical Material Only)

S93.1 Weld repair of the base metal by the material manufacturer or supplier is not permitted.

ADDITIONAL SUPPLEMENTARY REQUIREMENTS

Standardized supplementary requirements for use at the option of the purchaser are listed in Specification **A 6/A 6M** as follows:

S18. Maximum Tensile Strength (Grades 50 [345], 50S [345S], 50W [345W], and HPS 50W [HPS 345W]).

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A 709/A 709M – 08) that may impact the use of this standard. (Approved April 1, 2009.)

(1) Deleted Section 11 and Table 5 and renumbered subsequent sections and tables.

(2) Revised Sections **1, 2, 5-8, and 11-14.**
(3) Revised **Table 1, Table 8, and Table 9.**

Committee A01 has identified the location of selected changes to this standard since the last issue (A 709/A 709M – 07) that may impact the use of this standard. (Approved Oct. 1, 2008.)

(1) Revised **Table 8** and **Table 9.**

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).